

## DINITROL 440 – 441 – 445

### Body Work Protection Spray

#### Characteristics:

DINITROL 440-441-445 Dröhnex Spray is a synthetic resin/plastic-based product with anti-drone effect for stone chipping and bodywork protection. The easy-to-use spray is particularly designed for small repair tasks and the DIY sector.

#### Method of Use:

Before use, shake the can until the mixing ball can clearly be heard. (approx. 2 min). Spray the product onto the dry and dust, grease and oil-free surface in an even cross coat at a distance of 25 – 30 cm. For small surfaces, the product can also be sprayed in a circular movement. If applying thicker layers, allow to dry between coats. The material can be coated once dry. Depending on temperature, humidity and coat thickness, the spray is touch-dry in 30 minutes.

#### Technical properties:

Base:	Alkyd resin - synthetic
Colour:	Black, white, grey
Density:	1.1 g/ml (active agent)
Flash point:	< - 20 - 4°C (active agent)
Drying time: Touch dry at 20°C	Approx. 30 min / 50 µ
Solids content:	~ 40% (active agent)
Processing temperature:	15°C – 25°C
Propellant:	Propane/butane
Storage:	Cool and dry
Storage time:	24 months
Delivery form:	500 ml spray can (standard)
Hazard indication:	Highly flammable

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com