

# DINITROL<sup>®</sup> 447

## Protect Super Corrosion Protection

### Characteristics:

DINITROL 447 Protect Super is a fast-drying, rubber and resin based auto-body protection agent. Clearly higher rust protection is achieved through zinc additives. Zinc ions also prevent or delay rust formation in areas where the protective film is damaged. DINITROL 447 Protect Super contains no aggressive solvents such as chlorinated hydrocarbons (CFC/CHC), esters and ketones.

### Application fields:

The product is particularly well-suited for after-treatment of auto-bodies. DINITROL 447 Protect Super does not attack PVC coatings, is asbestos- and bitumen-free, permanently elastic and resists stone impact and road salt. After thorough drying, DINITROL 447 Protect Super can be coated with all conventional paints.

### Method of application:

DINITROL 447 Protect Super is sprayed onto the dry, dust- and grease-free surface evenly and in criss-cross pattern, using 4 - 6 bar air pressure and a customary gun for underbody protection. DINITROL 447 Protect Super can be painted over when thoroughly dry. Splashes can be removed with a benzene-soaked cloth.

### Technical properties:

Colour:	black / grey
Base:	resin / rubber
Spec. weight:	approx. 1 g/ml
Solids content:	approx. 50%
Working temperature:	10 – 25°C
Water solubility:	insoluble in water
Paintable:	after thorough drying
Salt spray test DIN 50021:	> 400 h
Storage period:	24 months
Form of supply:	1 l spray funnel bottle

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com